

US005512162A

United States Patent [19]

Sachs et al.

[11] Patent Number:

5,512,162

[45] Date of Patent:

Apr. 30, 1996

[54] METHOD FOR PHOTO-FORMING SMALL SHAPED METAL CONTAINING ARTICLES FROM POROUS PRECURSORS

[75] Inventors: **Emanuel Sachs**, Somerville; **Che-Chih Tsao**, Cambridge, both of Mass.

[73] Assignee: Massachusetts Institute of Technology, Cambridge, Mass.

[21] Appl. No.: 929,604

[22] Filed: Aug. 13, 1992

205/184, 187, 144, 150, 161, 170, 918, 123, 136; 427/212, 222, 214, 215, 216, 217, 243, 581, 595, 596, 597, 404, 304–306; 430/322, 325, 394, 396; 156/272.2, 272.8,

273.3, 273.9, 275.1; 118/620

[56] References Cited

U.S. PATENT DOCUMENTS

4,802,951 2/1989 Cla 5,071,337 12/1991 Hel 5,128,235 7/1992 Vas 5,133,987 7/1992 Spe 5,151,153 9/1992 Bol 5,182,170 1/1993 Ma	m et al
--	---------

OTHER PUBLICATIONS

Young, Wayne, "Multilayer Ceramic Technology" from Electronic Ceramics, properties, devices and applications; ed. Levinsen, L, Marcel Dekker, Inc., New York, N.Y. (1988).

Pearlstein, F., "Electroless Plating," *Modern Electroplating*, John Wiley & Sons, New York pp. 710–747 (1974).

F. L. Siegrist, "Have You Considered Electroforming?" Metal Progress, Oct. 1964, pp. 219–230.

F. L. Siegrist, "Electroforming with Nickel: A Versatile Production Technique," Metal Progress, Nov. 1964, pp. 121–130.

H. Reiche, W. W. Dunn, and A. J. Bard, "Heterogeneous Photocatalytic and Photosynthetic Deposition of Copper on TiO₂ and WO₃ Powders," Journal of Physical Chemistry, vol. 83, No. 17, 1979, p. 2248.

Y. C. Kiang, J. R. Moulic, and J. Zahavi, "Metal Silicide Formed by Laser Irradiation of Silicon Chip in Plating Solution," IBM Technical Disclosure Bulletin, vol. 26 No. 1,

(List continued on next page.)

Primary Examiner—John Niebling
Assistant Examiner—William T. Leader
Attorney, Agent, or Firm—Steven J. Weissburg

[57] ABSTRACT

The invention is a method for making a metal containing article, comprising the steps of: providing a layer of a porous ground in a selected area; exposing selected regions of the layer of porous ground to light, thereby metallizing the selected regions; repeating the foregoing steps a selected number of times to produce a selected number of layers; and selectively modifying the metallized regions of the layers. The initial metallization can be by electroless or semiconductor photo deposition plating. The subsequent modification of the metallized regions can be by electroless plating, electroplating or sintering. It is also possible, in some instances, to forego the second phase modification, the initial phase having provided the desired parameters. In a third preferred embodiment, the invention is a method using an initial metallization phase effected by exposure of a metal salt, such as a metal halide, to light, thereby inducing activation of the halide. A subsequent metallization step is conducted, as well as subsequent modification according to any of the methods mentioned above. A continuous embodiment of the invention is also disclosed, where a continuously deposited bed of powder particles is exposed to light and metallized. Subsequently, the metallized regions are further modified as above. An apparatus for the practice of the continuous methods is also proposed.

32 Claims, 10 Drawing Sheets

